



MYK LATICRETE Superset:

Providing and installing tiles or natural stones as per architectural requirement with MYK Laticrete Superset diluted with water and mixed with cement in Wet-on-Wet system.(Slurry System)

Use of white cement is recommended for white or light coloured natural stones. Dark coloured stones and all types of tiles may be installed using Grey cement mixed with Superset diluted with water.

Dosage: 300ml of Superset for each 50 Kg bag of cement.

Mixing ratio shall be as follows:

50 Kg cement : 300ml Superset: 20 Liters of Water.

For detailed installation and laying procedure follow MYK LATICRETE Method Statement.

Laticrete products supplied shall be as Manufactured by MYK LATICRETE India Pvt Ltd

Performance: Superset slurry:

MYK Laticrete SUPERSET mixed with Water and used with Cement as slurry: (Proportion: Cement: Water: Superset = 50 Kg: 20Ltrs: 300ml.)

Parameter	Traditional slurry method	Superset slurry method
Bond strength	0.25 To 0.50 MPa	0.50 to 0.75 MPa
Water Absorption	High	Low
Water segregation	Yes	No
Water curing	Required	Not required